

NanoDAC/fibDAC - Nanodeformation Measurement Techniques for Reliability Analysis of MEMS and NEMS

J. Keller^{***}, D. Vogel^{*} and B. Michel^{*}

^{*}Fraunhofer Institute for Reliability and Microintegration (IZM), Micro Materials Center, Gustav-Meyer-Allee 25, 13355 Berlin, Germany, juergen.keller@izm.fraunhofer.de

^{**}AMIC Angewandte Micro-Messtechnik GmbH, Volmerstraße 9B, 12489 Berlin, Germany

ABSTRACT

Recent advances in microtechnology and the development of new electronics and micro/nanosystem devices in aerospace and automotive industry, communication sector and life science have led to a strong need in material characterization on the micro and nano scale. Under this prerequisite Scanning Probe Microscopy (SPM) serves as the basis for the development of the nanoDAC method (nano Deformation Analysis by Correlation), which allows the determination and evaluation of 2D displacement fields based on SPM data. In addition to the nanoDAC method the fibDAC method provides similar accuracy. With the fibDAC (FIB, Focused Ion Beam) method the classical hole drilling method for residual stress measurement has been downscaled to the nanoscale. The ion beam of the FIB station is used as a milling tool which causes the stress release. With the combination of fibDAC and finite element analysis stresses of silicon microstructures of MEMS devices or at other pre-stressed materials or surface coatings can be determined.

Keywords: nanoDAC, fibDAC, nanodeformation, residual stress measurement

1 INTRODUCTION

With the demands for low cost electronics stacking and packaging of ICs is essential for the design of microelectronic systems. In addition to the IC and module level the integration on system level is achieved by embedded active and passive components. Regardless of the integration level thermo-mechanical challenges have to be solved due to the fact that material interfaces become even more important. Another challenge in electronic packaging is the integration of multiple device technologies such as digital, RF and MEMS, Optoelectronics on the same packaging platform [1]. Loading such structures thermally and/or mechanically means to stress the structure within submicron and nano-scale volumes caused by severe material mismatch. Therefore, actual loading causes local stresses and strains due to different material properties such as coefficient of thermal expansion (CTE), Young's modulus or time depended viscoelastic or creep properties. The smallest existing material imperfections or initial micro/nano-scale defects can grow under stress and strain

and can finally cause failure of the device. Due to these facts efforts have to be made to gain a better understanding of the material responses at submicron and nano scale and at material interfaces. The way to achieve this aim is the combination of displacement and strain measurements on the micro- and nano-scale with modeling techniques such as finite element analysis or molecular modeling. Under this prerequisite Scanning Probe Microscopy (SPM) serves as the basis for the development of the nanoDAC method (nano Deformation Analysis by Correlation), which allows the determination and evaluation of 2D displacement fields based on SPM data.

From the experimental point of view measurements of thermo-mechanically induced deformations and strains at the nano scale can be carried out by state of the art nanotechnological microscopy. Research on the combination of atomic force microscope (AFM) images and digital image correlation (DIC) algorithms proofs the ability to determine nanodisplacements at microelectronic components and MEMS. The authors of the paper made use of AFM equipment for deformation field measurement [2-5]. In this paper the underlying basic principles of the digital image correlation (DIC) method will be presented. The application of nanoscale displacement measurement technique on micro- and nanomaterials will be shown by a crack analysis of a thermoset polymer (cyanate ester thermoset) material. In addition the fibDAC method will be discussed (FIB, focused ion beam) which can be applied for residual stress measurement at the nanoscale.

2 NANODAC TECHNIQUE

Digital image correlation methods on gray scale images were established by several research groups. In previous research the authors developed and refined different tools and equipment in order to apply scanning electron microscopy (SEM) images for deformation analysis on thermo-mechanically loaded electronics packages. The respective technique was established as microDAC, which means micro Deformation Analysis by means of Correlation algorithms [6]. The microDAC technique is a method of digital image processing. Digitized micrographs of the analyzed objects in at least two or more different states (e.g. before and during/after mechanical or thermal loading) have to be obtained by means of an appropriate imaging technique. Generally, images extracted from a

variety of sources such as SEM or laser scanning microscopy (LSM) can be utilized for the application of digital cross correlation. The basic idea of the underlying mathematical algorithms follows from the fact that images commonly allow to record local and unique object patterns, within the more global object shape and structure. These patterns are maintained, if the objects are stressed by thermal or mechanical loading. In the case of atomic force microscopy (AFM) topography images structures (patterns) are obtained by the roughness of the analyzed object surface. Figure 1 shows examples of AFM topography images taken at a crack tip of a polymeric material.




Figure 1: AFM topography scans [$4.6 \mu\text{m} \times 4.6 \mu\text{m}$] at a crack tip of a polymer CT (compact tension) specimen; the scans are carried out at different load states; (the indentation near the crack tip is an indentation caused by a cantilever approach)

Markers indicate typical local patterns (i.e. topographic features) of the images. In most cases, these patterns are of stable appearance, even if severe load is applied to the specimens so that they can function as a local digital marker for the correlation algorithm. The cross correlation approach is the basis of the DIC technique. A scheme of the correlation principle is illustrated by Fig. 2.




Figure 2: Displacement evaluation by cross correlation algorithm; (left) detail of a reference image at load state 1; (right) detail of an image at load state 2 [7].

Images of the object are obtained at the reference load state 1 and at a different second load state 2. Both images are compared with each other using a cross correlation algorithm. In the image of load state 1 (reference) rectangular search structures (kernels) are defined around predefined grid nodes (Fig. 2, left). These grid nodes

represent the coordinates of the center of the kernels. The kernels themselves act as gray scale pattern from load state image 1 that have to be tracked, recognized and determined by its position in the load state image 2. In the calculation step the kernel window ($n \times n$ submatrix) is displaced inside the surrounding search window (search matrix) of the load state image 2 to find the position of best matching (Fig. 2, right). This position is determined by the maximum cross correlation coefficient which can be obtained for all possible kernel displacements within the search matrix. The described search algorithm leads to a two-dimensional discrete field of correlation coefficients defined at integer pixel coordinates. The discrete field maximum is interpreted as the location, where the reference matrix has to be shifted from the first to the second image, to find the best matching pattern. For enhancement of resolution a so-called subpixel analysis is implemented in the utilized software [7]. The two-dimensional cross correlation and subpixel analysis in the surroundings of a measuring point primarily gives the two components of the displacement vector. Applied to a set of measuring points (e.g. to a rectangular grid of points with a user defined pitch), this method allows to extract the complete in-plane displacement field. Commonly, graphical representations such as vector plots, superimposed virtual deformation grids or color scale coded displacement plots are implemented in commercially available or in in-house software packages [8, 9]. Finally, taking numerically derivatives of the obtained displacement fields $u_x(x,y)$ and $u_y(x,y)$ the in-plane strain components ϵ and the local rotation angle ρ are determined.

For images originating from scanning probe microscopy (SPM) techniques the described approach has been established as so-called nanoDAC method (nano Deformation Analysis by Correlation)[2]. This method is particularly suited for measurement of displacement fields with highest resolution focused on MEMS/NEMS devices and micro and nano-structural features of typical microelectronics materials.

In a typical nanodeformation measurement session in-situ AFM scans of the analyzed object are carried out at different thermo-mechanical load states as shown in Fig. 1. In the illustrated case an AFM topography signal serves as the image source. It is also possible to use other SPM imaging signals such as Phase Detection Microscopy or Ultrasonic Force Microscopy. The AFM scans are taken at the vicinity of a crack at a compact tension (CT) crack test specimen Fig. 3. The CT-specimen is loaded with the force F by a special tension/compression testing module so that a Mode I (opening) loading of the crack tip is enabled. Figure 3 shows the CT-specimen and parts of the loading device under the AFM.




Figure 3: (left) Compact tension (CT) specimen; (right) In-situ loading under the AFM.

For the images of the discussed loading of a thermoset polymer CT-specimen as given in Fig. 1 the extracted vertical (crack opening) displacement field is illustrated in Fig. 4.




Figure 4: Crack opening displacement field in vertical (y-) direction [μm] determined by means of nanoDAC; in the background of the contour lines the AFM topography scan of Fig. 1 (left) is illustrated.

Due to the application of SPM equipment deformations in the micro-, nanometer range can be easily detected. Currently the accuracy of the nanoDAC method for displacement field measurement is 1 nm for scan sizes of 2 μm , where the accuracy is determined by the thermo-mechanical stability of the SPM system. Details on the effect of thermal drifts and typical SPM related stability issues are discussed in [10]. In addition this reference shows compensation strategies for such error sources. The measurement technique can be performed on bulk materials, thin films and on devices i.e. microelectronic components, sensors or MEMS/NEMS. Furthermore, the

characterization and evaluation of micro- and nano-cracks or defects in bulk materials, thin layers and at material interfaces can be carried out.

3 FIBDAC TECHNIQUE

Measurement of residual stresses is an important demand for MEMS and sensor development. Loading of devices can produce stresses, which superpose with inherent residual stresses. In the case stresses with identical algebraic signs already small additional loads can lead to device damage. Furthermore, stress induced warpage of MEMS and sensor structures can be a severe problem. Because internal stresses cannot be measured directly as forces, indirect approaches have to be looked for. One classical method is the release of residual stresses by material removal and subsequent measurement of induced respective strains at the object surface. The method became established as hole-drilling strain gage method [11], where through or blind holes are processed mechanically into the material. Released strains are commonly measured by strain gages attached to the object surface. Unfortunately, mechanical or laser based material removal is restricted in size. Also strain gages can not be placed easily on the object surface of sensors or MEMS. For these reasons, FIB milling seems to be an effective tool to extend the hole-drilling approach to submicron or even nano scale. Accompanying FIB material removal with spatially high resolution deformation measurement methods like DIC or Moiré is another prerequisite to downscale the classical method to the micro and nano region.

The ion beam of the FIB station is used as a milling tool which causes the stress release at silicon microstructures of MEMS devices (Fig. 5).




Figure 5: FIBDAC; Stress release by ion milling in focused ion beam equipment (hole is milled by ion beam); Deformation field is analysed by Digital Image Correlation (DIC); Residual stresses can be evaluated

The analysis of the stress release is achieved by DIC applied to load state SEM images captured in cross beam equipment (combination of SEM and FIB). The results of the DIC analysis are deformation fields which are transferred to stress solution by application of finite element analysis. In another step the resolution of the

method has been improved by the application of trench milling instead of milling of holes [12]. Thereby the accuracy of the method has been improved.

4 CONCLUSIONS

With the presented methods the basis is provided for an experimental reliability analysis of MEMS/NEMS and nanodevices. In combination with numerical methods new strategies for life time evaluation and fatigue can be addressed.

ACKNOWLEDGEMENTS

The authors wish to acknowledge the collaboration with Jordi Puigcorbe and Neus Sabate from Departament d'Electronica, Universitat Barcelona, Spain.

REFERENCES

- [1] International Technology Roadmap for Semiconductors (ITRS) 2005 Edition Assembly and Packaging
- [2] Keller, J.; Vogel, D.; Schubert, A. and Michel, B.: Displacement and strain field measurements from SPM images, in *Applied Scanning Probe Methods*, B. Bhushan, H. Fuchs, and S. Hosaka, eds., pp. 253–276, Springer, 2004.
- [3] Vogel, D. and Michel, B.: Microcrack evaluation for electronics components by AFM nanoDAC deformation measurement, in *Proceedings of the 2001 1st IEEE Conference on Nanotechnology. IEEE-NANO 2001*, pp. 309–312, 2001.
- [4] Vogel, D.; Keller, J.; Gollhardt, A. and Michel, B.: Evaluating microdefect structures by AFM based deformation measurement, in *Proc. of SPIE Vol. 5045, Testing Reliability, and Application of Micro- and Nano-Materials Systems.*, pp. 1-12, 2003.
- [5] Puigcorbe, J.; Vogel, D.; Michel, B.; Vila, A. Gracia, I.; Cane, C. and Morante, J., *Journal of Micromechanics and Microengineering* 13(5), pp. 548-556, 2003.
- [6] D. Vogel, A. Schubert, W. Faust, R. Dudek, and B. Michel, *Microelectronics Reliability* 36(11-12), pp. 1939–1942, 1996.
- [7] Dost, M.; Kieselstein, E. and Erb, R., *Micromaterials and Nanomaterials* (1), pp. 30-35, 2002.
- [8] UNIDAC, Chemnitzer Werkstoffmechanik GmbH, www.cwm-chemnitz.de
- [9] ADASIM, Image Instruments GmbH, www.image-instruments.de/ADASIM/
- [10] Michel, B. and Keller, J.: Nanodeformation Analysis Near Small Cracks by Means of nanoDAC Technique in: G. Wilkening and L. Koenders (eds.) *Nanoscale Calibration Standards and Methods*, Wiley-VCH, Weinheim, pages 481-489, 2005.
- [11] Standard Test Method for Determining Residual Stresses by the Hole-Drilling Strain-Gage Method (E837-01e1), ASTM 2001.
- [12] N. Sabate; D. Vogel; A. Gollhardt; J. Keller; C. Cane; I. Gracia; J.R. Morante and B. Michel; *J. Micromech. Microeng.* 16 (2006) 254–259